

HIGH IMPACT POLYSTYRENE(HIPS)

SH 03

Characteristics:

- High flow
- Good melt strength
- · Excellent toughness

Processing:

Molding

Applications:

- Gas assisted injection molding of T.V cabinets.
- Suitable for thin walled parts, AC grills and toys
- Base material for compounding

Material Status : Commercial : Active
Agency Ratings : FDA 21 CFR 177.1640, UL File E185934

rigorioy riamigo .	15/12/ 6/11/11/16/16, 62/ 11/6 2/6666/			1 110 2 10000 1
PROPERTY	ASTM TEST METHOD	TEST CONDITION	VALUE	UNIT
Rheological				
Melt Flow Index	D1238	200°C / 5kgs	10	gm / 10 min
Thermal				
Vicat Softening Point HDT (Unannealed)	D1525 D648	1kg/ 120 °C 18.564 kg/cm²	97 76	°C °C
Mechanical				
Tensile Strength Elongation Flexural Strength Flexural Modulus Izod Impact (Notched)	D638 D638 D790 D790 D256	50 mm/min. 50 mm/min. 3.2 mm 3.2 mm 3.2 mm	220 50 370 18000 100	Kg / cm² % Kg / cm² Kg / cm² J/m
Flammability				
Glow wire temperature Flammability	IEC 695-2-1 UL 94	- @ 1.6mm	- HB	°C -
General				
Specific Gravity	D792	-	1.03	-
Processing Conditions				
Melt temp. Pre drying temp. Mold temp.	- - -	- - -	180-260 NA 40-60	°C °C °C

Data presented in this catalogue is typical values of properties and intended to serve as guide only. SPL reserves the right to review the content of this catalogue and revise.











Test Method & Standard Properties

Data presented in this catalogue is typical values of properties for natural material and intended to ser ve as a guide only. All tests are carried out at 23°C unless otherwise stated. Testing of all mechanical properties is done with injection moulded specimen of 3.2 mm. In actual applications, properties can be affected to a considerable extent by the mould / die design, the processing conditions and the colour .

Environmental

Supreme polystyrene resins can be recycled, incinerated or disposed off in landfill without detriment to the environment. Adequate ventilation should be used during processing. Where recycling of Supreme Polystyrene is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Material Safety Data Sheets (MSDS) for Supreme Polystyrene resins are available from Supreme Petrochem Ltd. MSD sheets are provided to help customers their own handling, safety and disposal needs, and those that may be required for applicable health and safety regulations e.g. OSHA, ISO14000.

Supreme flame retardant polystyrene grades contains additives which may release hazardous or toxic vapors at given lengthy or excessive exposure to high heat. Kindly, refer to recommended processing temperatures and use suitable personal protective equipments.

Handling Precautions

While the handling of Supreme polystyrene pellets generally does not present unusual problems, a dust can be formed under some circumstances. If workers are exposed to this dus, they should be protected from dust inhalation by use of approved dust respirators. Contact with the skin and eyes should be prevented by use of protective equipment and/orclothing.

SPL recommends storing of polystyrene in cool & dry place in a shade away from sunlight and heat. The packing used is not UV stabilised and hence should not be exposed to sunlight.

Exclusion of Liability

The information contained herein is provided for general reference purposes only. By providing the information contained herein, Supreme Petrochem Ltd. makes no guaranty or warranty, and does not assume any liability, with respect to the accuracy or completeness of such information, or the product results in any specific instance and hereby expressly disclaims any implied warranties of merchantability or fitness for a particular purpose, or any other warranties or representations whatsoever, expressed or implied. Nothing contained herein shall be construed as a licence to use the products of Supreme Petrochem Itd in any manner that would infringe any patent.





